

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

D-1

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | |
|---|-----------|---|
| (51) International Patent Classification 6: C11D 7/50 | A1 | (11) International Publication Number: WO 96/22356 (43) International Publication Date: 25 July 1996 (25.07.96) |
| <p>(21) International Application Number: PCT/US96/00336</p> <p>(22) International Filing Date: 11 January 1996 (11.01.96)</p> <p>(30) Priority Data: 08/375,812 20 January 1995 (20.01.95) US 08/573,416 15 December 1995 (15.12.95) US</p> <p>(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> <p>(72) Inventors: FLYNN, Richard, M.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). GRENFELL, Mark, W.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MOORE, George, G., I.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). OWENS, John, G.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> <p>(74) Agents: WEISS, Lucy, C. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> | | <p>(81) Designated States: CA, CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p> |
| <p>(54) Title: CLEANING PROCESS AND COMPOSITION</p> <p>(57) Abstract</p> <p>A process for removing contaminants from the surface of a substrate comprises contacting the substrate with a cleaning composition comprising at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound, the compound optionally containing additional catenary heteroatoms. The compounds exhibit good solvency properties while being environmentally acceptable.</p> | | |

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | |
|----|--------------------------|----|---------------------------------------|----|--------------------------|
| AM | Armenia | GB | United Kingdom | MW | Malawi |
| AT | Austria | GE | Georgia | MX | Mexico |
| AU | Australia | GN | Guinea | NE | Niger |
| BB | Barbados | GR | Greece | NL | Netherlands |
| BE | Belgium | HU | Hungary | NO | Norway |
| BF | Burkina Faso | IE | Ireland | NZ | New Zealand |
| BG | Bulgaria | IT | Italy | PL | Poland |
| BJ | Benin | JP | Japan | PT | Portugal |
| BR | Brazil | KE | Kenya | RO | Romania |
| BY | Belarus | KO | Kyrgyzstan | RU | Russian Federation |
| CA | Canada | KP | Democratic People's Republic of Korea | SE | Sweden |
| CF | Central African Republic | KR | Republic of Korea | SG | Singapore |
| CG | Congo | KZ | Kazakhstan | SI | Slovenia |
| CH | Switzerland | LI | Liechtenstein | SK | Slovakia |
| CI | Cote d'Ivoire | LK | Sri Lanka | SN | Senegal |
| CN | China | LT | Lithuania | SE | Sweden |
| CS | Czechoslovakia | LU | Luxembourg | TD | Chad |
| CZ | Czech Republic | LV | Latvia | TG | Togo |
| DE | Germany | MC | Monaco | TJ | Tajikistan |
| DK | Denmark | MD | Republic of Moldova | TT | Trinidad and Tobago |
| EE | Estonia | MG | Madagascar | UA | Ukraine |
| ES | Spain | ML | Mali | UG | Uganda |
| FI | Finland | MN | Mongolia | US | United States of America |
| FR | France | MR | Mauritania | UZ | Uzbekistan |
| GA | Gabon | | | VN | Viet Nam |

WO 96/22356

PCT/US96/00336

CLEANING PROCESS AND COMPOSITION

5

Field of the Invention

This invention relates to cleaning compositions comprising at least one partially-fluorinated ether compound and to processes for removing contaminants from substrate surfaces using such compositions. In another aspect, this invention relates to certain novel partially-fluorinated ether compounds. In yet another aspect, this invention relates to coating compositions comprising at least one partially-fluorinated ether compound and to processes for depositing coatings on substrate surfaces using such compositions.

20 Background of the Invention

Solvent cleaning applications where contaminated articles are immersed in (or washed with) solvent liquids and/or vapors are well-known. Applications involving one or more stages of immersion, rinsing, and/or drying are common. Solvents can be used at ambient temperature (often, accompanied by ultrasonic agitation) or at elevated temperatures up to the boiling point of the solvent.

A major concern in solvent cleaning is the tendency (especially where solvent is used at an elevated temperature) for solvent vapor loss from the cleaning system into the atmosphere. Although care is generally exercised to minimize such losses (e.g.,

WO 96/22356

PCT/US96/00336

through good equipment design and vapor recovery systems), most practical cleaning applications result in some loss of solvent vapor into the atmosphere.

Solvent cleaning processes have traditionally
5 utilized chlorinated solvents (e.g.,
chlorofluorocarbons such as 1,1,2-trichloro-1,2,2-
trifluoroethane and chlorocarbons such as 1,1,1-
trichloroethane) alone or in admixture with one or more
cosolvents such as aliphatic alcohols or other low
10 molecular weight, polar compounds. Such solvents were
initially believed to be environmentally-benign, but
have now been linked to ozone depletion. According to
the Montreal Protocol and its attendant amendments,
production and use of the solvents must be discontinued
15 (see, e.g., P. S. Zurer, "Looming Ban on Production of
CFCs, Halons Spurs Switch to Substitutes," Chemical &
Engineering News, page 12, November 15, 1993).

Thus, there has developed a need in the art
for substitutes or replacements for the commonly-used
20 cleaning solvents. Such substitutes should have a low
ozone depletion potential, should have boiling ranges
suitable for a variety of solvent cleaning
applications, and should have the ability to dissolve
both hydrocarbon-based and fluorocarbon-based soils.
25 Preferably, substitutes will also be low in toxicity,
have no flash points (as measured by ASTM D3278-89),
have acceptable stability for use in cleaning
applications, and have short atmospheric lifetimes and
low global warming potentials.

30 Partially-fluorinated ethers have been
suggested as chlorofluorocarbon alternatives (see,
e.g., Yamashita et al., International Conference on CFC
and BFC (Halons), Shanghai, China, August 7-10, 1994,
pages 55-58).

WO 96/22356

PCT/US96/00336

European Patent Publication No. 0 450 855 A2
(Imperial Chemical Industries PLC) describes the use of
low molecular weight, fluorine-containing ethers of
boiling point 20-120°C in solvent cleaning applications.

5 International Patent Publication No.
WO 93/11280 (Allied-Signal, Inc.) discloses a non-
aqueous cleaning process which utilizes a fluorocarbon-
based rinsing solvent.

10 U.S. Patent No. 5,275,669 (Van Der Puy et
al.) describes hydrofluorocarbon solvents useful for
dissolving contaminants or removing contaminants from
the surface of a substrate. The solvents have 4 to 7
carbon atoms and have a portion which is fluorocarbon,
the remaining portion being hydrocarbon.

15 U.S. Patent No. 3,453,333 (Litt et al.)
discloses fluorinated ethers containing at least one
halogen substituent other than fluorine and states that
those ethers which are liquid can be used as solvents
for high molecular weight resinous perhalogenated
20 compounds such as solid polychlorotrifluoroethylene
resins.

French Patent Publication No. 2,287,432
(Societe Nationale des Poudres et Explosifs) describes
new partially-fluorinated ethers and a process for
25 their preparation. The compounds are said to be useful
as hypnotic and anesthetic agents; as monomers for
preparing heat-stable, fire-resistant, or self-
lubricant polymers; and in phyto-sanitary and phyto-
pharmaceutical fields.

30 German Patent Publication No. 1,294,949
(Farbwerke Hoechst AG) describes a technique for the
production of perfluoroalkyl-alkyl ethers, said to be
useful as narcotics and as intermediates for the
preparation of narcotics and polymers.

35

WO 96/22356

PCT/US96/00336

Summary of the Invention

In one aspect, this invention provides a process for removing contaminants (e.g., hydrocarbons, fluorocarbons, or even water) from the surface of a substrate (e.g., metal, glass, ceramic, plastic, or fabric). The process comprises contacting the substrate with (or exposing the substrate to) a liquid- and/or vapor-phase cleaning composition comprising at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound. The compound can optionally contain additional catenary (i.e., in-chain) heteroatoms (e.g., oxygen or nitrogen) and preferably has a boiling point in the range of from about 25°C to about 200°C.

The alkoxy-substituted compounds used in the process of the invention exhibit unexpectedly high stabilities in the presence of acids, bases, and oxidizing agents. In addition, in spite of their fluorine content, the compounds are surprisingly good solvents for hydrocarbons (as well as fluorocarbons). The compounds are low in toxicity and flammability, have ozone depletion potentials of zero, and have short atmospheric lifetimes and low global warming potentials relative to chlorofluorocarbons and many chlorofluorocarbon substitutes. Since the compounds exhibit good solvency properties while being environmentally acceptable, they satisfy the need in the art for substitutes or replacements for the commonly-used cleaning solvents which have been linked to the destruction of the earth's ozone layer.

In other aspects, this invention also provides certain novel mono-, di-, and trialkoxy-substituted perfluorocompounds; a cleaning composition;

a coating composition; and a process for depositing coatings (e.g., coatings of lubricant) on substrate surfaces.

5 Detailed Description of the Invention

Compounds which can be utilized in the processes of the invention are mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing
10 perfluoroalkane, and perfluorocycloalkylene-containing perfluoroalkane compounds. The compounds include those which contain additional catenary heteroatoms (as well as those which do not) and can be utilized alone, in combination with one another, or in combination with
15 other common cleaning solvents (e.g., alcohols, ethers, alkanes, alkenes, perfluorocarbons, perfluorinated tertiary amines, perfluoroethers, cycloalkanes, esters, ketones, aromatics, siloxanes, hydrochlorocarbons, hydrochlorofluorocarbons, and hydrofluorocarbons). The
20 compounds can be solids or liquids under ambient conditions of temperature and pressure, but are generally utilized for cleaning in either the liquid or the vapor state (or both). Thus, normally solid compounds can be utilized after transformation to liquid
25 and/or vapor through melting, sublimation, or dissolution in liquid co-solvent.

A class of useful alkoxy-substituted perfluorocompounds is that which can be represented by the following general formula (I):

30



wherein x is an integer of 1 to 3; when x is 1, R_f is selected from the group consisting of linear or branched perfluoroalkyl groups having from 2 to about
35 15 carbon atoms, perfluorocycloalkyl-containing

WO 96/22356


PCT/US96/00336

- perfluoroalkyl groups having from 5 to about 15 carbon atoms, and perfluorocycloalkyl groups having from 3 to about 12 carbon atoms; when x is 2, R_1 is selected from the group consisting of linear or branched
- 5 perfluoroalkanediyl groups or perfluoroalkylidene groups having from 2 to about 15 carbon atoms, perfluorocycloalkyl- or perfluorocycloalkylene-containing perfluoroalkanediyl or perfluoroalkylidene groups having from 6 to about 15 carbon atoms, and
- 10 perfluorocycloalkanediyl groups or perfluorocycloalkylidene groups having from 3 to about 12 carbon atoms; when x is 3, R_1 is selected from the group consisting of linear or branched
- 15 perfluoroalkanetriyl groups having from 2 to about 15 carbon atoms, perfluorocycloalkyl- or perfluorocycloalkylene-containing perfluoroalkanetriyl groups having from 6 to about 15 carbon atoms, and perfluorocycloalkanetriyl groups having from 3 to about 12 carbon atoms; each R_n is independently selected from
- 20 the group consisting of linear or branched alkyl groups having from 1 to about 8 carbon atoms, cycloalkyl-containing alkyl groups having from 4 to about 8 carbon atoms, and cycloalkyl groups having from 3 to about 8 carbon atoms; wherein either or both of the groups R_1 and R_n can contain (optionally contain) one or more
- 25 catenary heteroatoms; and wherein the sum of the number of carbon atoms in R_1 and the number of carbon atoms in R_n is greater than or equal to 4. The perfluorocycloalkyl and perfluorocycloalkylene groups
- 30 contained within the perfluoroalkyl, perfluoroalkanediyl, perfluoroalkylidene and perfluoroalkanetriyl groups can optionally (and independently) be substituted with, e.g., one or more perfluoroalkyl groups having from 1 to about 4 carbon
- 35 atoms.

WO 96/22356








PCT/US96/00336

- Preferably, x is 1; R_1 is as defined above; R_2 is an alkyl group having from 1 to about 6 carbon atoms; R_3 but not R_4 can contain one or more catenary heteroatoms; and the sum of the number of carbon atoms in R_1 and the number of carbon atoms in R_2 is greater than or equal to 4. Most preferably, x is 1; R_1 is selected from the group consisting of linear or branched perfluoroalkyl groups having from 3 to about 6 carbon atoms, perfluorocycloalkyl-containing perfluoroalkyl or perfluoroalkylidene groups having from 5 to about 8 carbon atoms, and perfluorocycloalkyl groups having from 5 to about 6 carbon atoms; R_4 is an alkyl group having from 1 to about 3 carbon atoms; R_5 but not R_6 can contain one or more catenary heteroatoms; and the sum of the number of carbon atoms in R_1 and the number of carbon atoms in R_4 is greater than or equal to 4. The perfluorocycloalkyl and perfluorocycloalkylene groups contained within the perfluoroalkyl, perfluoroalkanediyl, perfluoroalkylidene and perfluoroalkanetriyl groups can optionally (and independently) be substituted with, e.g., one or more perfluoromethyl groups. These compounds are preferred due to their ease of preparation and their performance characteristics.
- Representative examples of alkoxy-substituted perfluorocompounds suitable for use in the processes of the invention include the following compounds:



WO 96/22356

PCT/US96/00336



and 1,1-dimethoxyperfluorocyclohexane, where cyclic structures having an interior "F" are perfluorinated.

A novel subclass of the alkoxy-substituted perfluorocompounds is that which can be represented by the following general formula (II):






wherein R_f^1 and R_f^2 are both substituted or unsubstituted perfluoroalkyl groups having from 1 to about 6 carbon atoms or are both substituted or unsubstituted perfluoroalkylene groups having from 2 to about 4 carbon atoms, the perfluoroalkylene groups being bonded to one another to form a ring; y is an integer of 1 to about 8; C_yF_{2y} can be linear or branched; and R_h is selected from the group consisting of linear or branched alkyl groups having from 1 to about 8 carbon atoms, cycloalkyl-containing alkyl groups having from 4 to about 8 carbon atoms, and cycloalkyl groups having from 3 to about 8 carbon atoms; wherein the groups R_f^1 , R_f^2 , and R_h can optionally (and independently) contain one or more catenary heteroatoms.

Preferably, the perfluoroalkyl groups have from 1 to about 3 carbon atoms, the perfluoroalkylene groups have from 2 to about 3 carbon atoms; y is an integer of 1 to about 3; R_h is selected from the group consisting of linear or branched alkyl groups having from 1 to about 6 carbon atoms; and R_f^1 and R_f^2 but not R_h can independently contain one or more catenary heteroatoms. These compounds are preferred due to their ease of preparation and their performance characteristics.


Representative examples of novel compounds according to Formula II above include the following compounds:

WO 96/22356

PCT/US96/00336



A second novel subclass of the alkoxy-substituted perfluorocompounds is that which can be represented by the following general formula (III):
















wherein R_f^3 is a substituted or unsubstituted perfluorocycloalkyl, perfluorocycloalkanediyl, or perfluorocycloalkanetriyl group having from 3 to about 12 carbon atoms; each R_n is independently selected from the group consisting of linear or branched alkyl groups having from 1 to about 8 carbon atoms, cycloalkyl-containing alkyl groups having from 4 to about 8 carbon atoms, and cycloalkyl groups having from 3 to about 8 carbon atoms; and x' is an integer of 1 to 3; wherein either or both of the groups R_f^3 and R_n can contain (optionally contain) one or more catenary heteroatoms.

Preferably, R_f^3 has from 5 to about 6 carbon atoms; each R_n is independently selected from the group consisting of linear or branched alkyl groups having from 1 to about 6 carbon atoms; x' is an integer of 1 or 2; and R_f^3 but not R_n can contain one or more catenary heteroatoms. These compounds are preferred due to their ease of preparation and their performance characteristics.

Representative examples of novel compounds according to Formula III above include the following compounds:

WO 96/22356

PCT/US96/00336



5

The alkoxy-substituted perfluorocompounds suitable for use in the process of the invention can be prepared by alkylation of perfluorinated alkoxides prepared by the reaction of the corresponding

10 perfluorinated acyl fluoride or perfluorinated ketone with an anhydrous alkali metal fluoride (e.g., potassium fluoride or cesium fluoride) or anhydrous

WO 96/22356

PCT/US96/00336

silver fluoride in an anhydrous polar, aprotic solvent. (See, e.g., the preparative methods described in French Patent Publication No. 2,287,432 and German Patent Publication No. 1,294,949, supra.) Alternatively, a fluorinated tertiary alcohol can be allowed to react with a base, e.g., potassium hydroxide or sodium hydride, to produce a perfluorinated tertiary alkoxide which can then be alkylated by reaction with alkylating agent.

10 Suitable alkylating agents for use in the preparation include dialkyl sulfates (e.g., dimethyl sulfate), alkyl halides (e.g., methyl iodide), alkyl p-toluenesulfonates (e.g., methyl p-toluenesulfonate), alkyl perfluoroalkanesulfonates (e.g., methyl
15 perfluoromethanesulfonate), and the like. Suitable polar, aprotic solvents include acyclic ethers such as diethyl ether, ethylene glycol dimethyl ether, and diethylene glycol dimethyl ether; carboxylic acid esters such as methyl formate, ethyl formate, methyl
20 acetate, diethyl carbonate, propylene carbonate, and ethylene carbonate; alkyl nitriles such as acetonitrile; alkyl amides such as N,N-dimethylformamide, N,N-diethylformamide, and N-methylpyrrolidone; alkyl sulfoxides such as dimethyl
25 sulfoxide; alkyl sulfones such as dimethylsulfone, tetramethylene sulfone, and other sulfolanes; oxazolidones such as N-methyl-2-oxazolidone; and mixtures thereof.

Perfluorinated acyl fluorides (for use in
30 preparing the alkoxy-substituted perfluorocompounds) can be prepared by electrochemical fluorination (ECF) of the corresponding hydrocarbon carboxylic acid (or a derivative thereof), using either anhydrous hydrogen fluoride (Simons ECF) or KF.2HF (Phillips ECF) as the
35 electrolyte. Perfluorinated acyl fluorides and

WO 96/22356

PCT/US96/00336

perfluorinated ketones can also be prepared by dissociation of perfluorinated carboxylic acid esters (which can be prepared from the corresponding hydrocarbon or partially-fluorinated carboxylic acid esters by direct fluorination with fluorine gas). Dissociation can be achieved by contacting the perfluorinated ester with a source of fluoride ion under reacting conditions (see the method described in U.S. Patent No. 3,900,372 (Childs)) or by combining the ester with at least one initiating reagent selected from the group consisting of gaseous, non-hydroxylic nucleophiles; liquid, non-hydroxylic nucleophiles; and mixtures of at least one non-hydroxylic nucleophile (gaseous, liquid, or solid) and at least one solvent which is inert to acylating agents.

Initiating reagents which can be employed in the dissociation are those gaseous or liquid, non-hydroxylic nucleophiles and mixtures of gaseous, liquid, or solid, non-hydroxylic nucleophile(s) and solvent (hereinafter termed "solvent mixtures") which are capable of nucleophilic reaction with perfluorinated esters. The presence of small amounts of hydroxylic nucleophiles can be tolerated. Suitable gaseous or liquid, non-hydroxylic nucleophiles include dialkylamines, trialkylamines, carboxamides, alkyl sulfoxides, amine oxides, oxazolidones, pyridines, and the like, and mixtures thereof. Suitable non-hydroxylic nucleophiles for use in solvent mixtures include such gaseous or liquid, non-hydroxylic nucleophiles, as well as solid, non-hydroxylic nucleophiles, e.g., fluoride, cyanide, cyanate, iodide, chloride, bromide, acetate, mercaptide, alkoxide, thiocyanate, azide, trimethylsilyl difluoride, bisulfite, and bifluoride anions, which can be utilized in the form of alkali metal, ammonium, alkyl-

substituted ammonium (mono-, di-, tri-, or tetra-substituted), or quaternary phosphonium salts, and mixtures thereof. Such salts are in general commercially available but, if desired, can be prepared by known methods, e.g., those described by M. C. Sneed and R. C. Brasted in Comprehensive Inorganic Chemistry, Volume Six (The Alkali Metals), pages 61-64, D. Van Nostrand Company, Inc., New York (1957), and by H. Kobler et al. in Justus Liebigs Ann. Chem. 1978, 1937.

1,4-diazabicyclo[2.2.2]octane and the like are also suitable solid nucleophiles.

The cleaning process of the invention can be carried out by contacting a contaminated substrate with a cleaning composition comprising at least one of the above-described alkoxy-substituted perfluorocompounds. The perfluorocompounds can be utilized alone or in admixture with each other or with other commonly-used cleaning solvents, e.g., alcohols, ethers, alkanes, alkenes, perfluorocarbons, perfluorinated tertiary amines, perfluoroethers, cycloalkanes, esters, ketones, aromatics, siloxanes, hydrochlorocarbons, hydrochlorofluorocarbons, and hydrofluorocarbons. Such co-solvents can be chosen to modify or enhance the solvency properties of a cleaning composition for a particular use and can be utilized in ratios (of co-solvent to perfluorocompound(s)) such that the resulting composition has no flash point. Preferably, the perfluorocompound(s) used in the composition have boiling points in the range of from about 25°C to about 200°C, more preferably from about 25°C to about 125°C.

The cleaning composition can be used in either the gaseous or the liquid state (or both), and any of the known techniques for "contacting" a substrate can be utilized. For example, a liquid cleaning composition can be sprayed or brushed onto the

WO 96/22336

PCT/US96/00336

substrate, a gaseous cleaning composition can be blown across the substrate, or the substrate can be immersed in either a gaseous or a liquid composition. Elevated temperatures, ultrasonic energy, and/or agitation can be used to facilitate the cleaning. Various different solvent cleaning techniques are described by B. N. Ellis in Cleaning and Contamination of Electronics Components and Assemblies, Electrochemical Publications Limited, Ayr, Scotland, pages 182-94 (1986).

Both organic and inorganic substrates can be cleaned by the process of the invention. Representative examples of the substrates include metals; ceramics; glass; polycarbonate; polystyrene; acrylonitrile-butadiene-styrene copolymer; natural fibers (and fabrics derived therefrom) such as cotton, silk, fur, suede, leather, linen, and wool; synthetic fibers (and fabrics) such as polyester, rayon, acrylics, nylon, and blends thereof; fabrics comprising a blend of natural and synthetic fibers; and composites of the foregoing materials. The process is especially useful in the precision cleaning of electronic components (e.g., circuit boards), optical or magnetic media, and medical devices.

The cleaning process of the invention can be used to dissolve or remove most contaminants from the surface of a substrate. For example, materials such as light hydrocarbon contaminants; higher molecular weight hydrocarbon contaminants such as mineral oils and greases; fluorocarbon contaminants such as perfluoropolyethers, bromotrifluoroethylene oligomers (gyroscope fluids), and chlorotrifluoroethylene oligomers (hydraulic fluids, lubricants); silicone oils and greases; solder fluxes; particulates; and other contaminants encountered in precision, electronic, metal, and medical device cleaning can be removed.

The process is particularly useful for the removal of hydrocarbon contaminants (especially, light hydrocarbon oils), fluorocarbon contaminants, particulates, and water (as described in the next paragraph).

5 To displace or remove water from substrate surfaces, the cleaning process of the invention can be carried out as described in U.S. Patent No. 5,125,978 (Flynn et al.) by contacting the surface of an article with a liquid cleaning composition which preferably
10 contains a non-ionic fluoroaliphatic surface active agent. The wet article is immersed in the liquid composition and agitated therein, the displaced water is separated from the liquid composition, and the resulting water-free article is removed from the liquid
15 composition. Further description of the process and the articles which can be treated are found in said U.S. Patent No. 5,125,978. The process can also be carried out as described in U.S. Patent No. 3,903,012 (Brandreth).

20 This invention also provides a cleaning composition comprising (a) a major amount (preferably, at least about 60 percent of the composition by weight) of at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane,
25 perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound, the compound optionally containing additional catenary heteroatoms; and (b) a minor amount of at least one co-solvent selected from the group consisting
30 of alcohols, ethers, alkanes, alkenes, perfluorocarbons, perfluorinated tertiary amines, perfluoroethers, cycloalkanes, esters, ketones, aromatics, siloxanes, hydrochlorocarbons, hydrochlorofluorocarbons, and hydrofluorocarbons.
35 Preferably, the co-solvent is selected from the group

WO 96/22356

PCT/US96/00336

consisting of alcohols, alkanes, alkenes, cycloalkanes, esters, aromatics, hydrochlorocarbons, and hydrofluorocarbons.

Representative examples of co-solvents which
5 can be used in the cleaning composition include methanol, ethanol, isopropanol, t-butyl alcohol, methyl t-butyl ether, methyl t-amyl ether, 1,2-dimethoxyethane, cyclohexane, 2,2,4-trimethylpentane, n-decane, terpenes (e.g., α -pinene, camphene, and
10 limonene), trans-1,2-dichloroethylene, methylcyclopentane, decalin, methyl decanoate, t-butyl acetate, ethyl acetate, diethyl phthalate, 2-butanone, methyl isobutyl ketone, naphthalene, toluene, p-chlorobenzotrifluoride, trifluorotoluene, hexamethyl
15 disiloxane, octamethyl trisiloxane, perfluorohexane, perfluoroheptane, perfluorooctane, perfluorotributylamine, perfluoro-N-methyl morpholine, perfluoro-2-butyl oxacyclopentane, methylene chloride, chlorocyclohexane, 1-chlorobutane, 1,1-dichloro-1-
20 fluoroethane, 1,1,1-trifluoro-2,2-dichloroethane, 1,1,1,2,2-pentafluoro-3,3-dichloropropane, 1,1,2,2,3-pentafluoro-1,3-dichloropropane, 2,3-dihydroperfluoropentane, 1,1,1,2,2,4-hexafluorobutane, 1-trifluoromethyl-1,2,2-trifluorocyclobutane, 3-methyl-
25 1,1,2,2-tetrafluorocyclobutane, and 1-hydropentadecafluoroheptane.

The above-described alkoxy-substituted perfluorocompounds can be useful not only in cleaning but also in coating deposition, where the
30 perfluorocompound functions as a carrier for a coating material to enable deposition of the material on the surface of a substrate. The invention thus also provides a coating composition and a process for depositing a coating on a substrate surface using the
35 composition. The process comprises the step of

applying to at least a portion of at least one surface of a substrate a coating of a liquid coating composition comprising (a) a solvent composition comprising at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound, the compound optionally containing additional catenary heteroatoms; and (b) at least one coating material which is soluble or dispersible in the solvent composition. The solvent composition can further comprise one or more co-dispersants or co-solvents (as defined supra, preferably those having boiling points below about 125°C) and/or one or more additives (e.g., surfactants, coloring agents, stabilizers, anti-oxidants, flame retardants, and the like). Preferably, the process further comprises the step of removing the solvent composition from the coating by, e.g., allowing evaporation (which can be aided by the application of, e.g., heat or vacuum).

Coating materials which can be deposited by the process include pigments, lubricants, stabilizers, adhesives, anti-oxidants, dyes, polymers, pharmaceuticals, release agents, inorganic oxides, and the like, and combinations thereof. Preferred materials include perfluoropolyether, hydrocarbon, and silicone lubricants; amorphous copolymers of tetrafluoroethylene; polytetrafluoroethylene; and combinations thereof. Representative examples of materials suitable for use in the process include titanium dioxide, iron oxides, magnesium oxide, perfluoropolyethers, polysiloxanes, stearic acid, acrylic adhesives, polytetrafluoroethylene, amorphous copolymers of tetrafluoroethylene, and combinations thereof. Any of the substrates described above (for

cleaning applications) can be coated via the process of the invention. The process can be particularly useful for coating magnetic hard disks or electrical connectors with perfluoropolyether lubricants or
5 medical devices with silicone lubricants.

To form a coating composition, the components of the composition (i.e., the alkoxy-substituted perfluorocompound(s), the coating material(s), and any co-dispersant(s) or co-solvent(s) utilized) can be
10 combined by any conventional mixing technique used for dissolving, dispersing, or emulsifying coating materials, e.g., by mechanical agitation, ultrasonic agitation, manual agitation, and the like. The solvent composition and the coating material(s) can be combined
15 in any ratio depending upon the desired thickness of the coating, but the coating material(s) preferably constitute from about 0.1 to about 10 weight percent of the coating composition for most coating applications.

The deposition process of the invention can
20 be carried out by applying the coating composition to a substrate by any conventional technique. For example, the composition can be brushed or sprayed (e.g., as an aerosol) onto the substrate, or the substrate can be spin-coated. Preferably, the substrate is coated by
25 immersion in the composition. Immersion can be carried out at any suitable temperature and can be maintained for any convenient length of time. If the substrate is a tubing, such as a catheter, and it is desired to ensure that the composition coats the lumen wall, it
30 may be advantageous to draw the composition into the lumen by the application of reduced pressure.

After a coating is applied to a substrate, the solvent composition can be removed from the coating by evaporation. If desired, the rate of evaporation
35 can be accelerated by application of reduced pressure

or mild heat. The coating can be of any convenient thickness, and, in practice, the thickness will be determined by such factors as the viscosity of the coating material, the temperature at which the coating is applied, and the rate of withdrawal (if immersion is utilized).

Objects and advantages of this invention are further illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention.

Examples

The environmental impact of the alkoxy-substituted perfluorocompounds used in the processes and compositions of the invention was assessed by determination of the atmospheric lifetime and the global warming potential (GWP) of certain compounds, as described below:

Atmospheric Lifetime

The atmospheric lifetime (t_{atm}) of various sample compounds was calculated by the technique described in Y. Tang, Atmospheric Fate of Various Fluorocarbons, M.S. Thesis, Massachusetts Institute of Technology (1993). According to this technique, an ultraviolet (UV) gas cell was charged with a sample compound, a reference compound (either CH_4 or CH_3Cl), ozone, and water vapor. Hydroxyl radicals were then generated by photolytic decomposition of the ozone in the presence of the water vapor and an inert buffer gas, i.e., helium. As the sample compounds and reference compounds reacted with the hydroxyl radicals in the gas phase, their concentrations were measured by Fourier

WO 96/22356

PCT/US96/00336

transform infrared spectroscopy (FTIR). The rate constant for reaction of the sample compound (k_{sample}) with hydroxyl radical was measured relative to the rate constant for a reference compound (k_{ref}), and the atmospheric lifetime was then calculated using the following formula (where t_{CH_4} and k_{CH_4} are known values):

10
$$\tau_{\text{sample}} = \frac{\tau_{\text{CH}_4}}{\left(\frac{k_{\text{sample}}}{k_{\text{ref}}} \right) \left(\frac{k_{\text{ref}}}{k_{\text{CH}_4}} \right)}$$

The rate constant for each sample compound was measured (using CH_4 as the reference compound and again using CH_3Cl) at 298K, and the atmospheric lifetime values were calculated and then averaged. The results are shown in Table A under the heading "Atmospheric Lifetime." For comparative purposes, the atmospheric lifetime for several hydrofluorocarbons is also shown in Table A.

20 Atmospheric lifetime was also estimated from a correlation developed between the highest occupied molecular orbital (HOMO) energy and the known atmospheric lifetimes of hydrofluorocarbons and hydrofluorocarbon ethers, in a manner similar to that described by Cooper et al. in Atmos. Environ. 26A, 7, 1331 (1992). The correlation differed from that found in Cooper et al. in the following respects: the correlation was developed using a larger data set; lifetimes for the correlations were determined by relative hydroxyl reactivity of the sample to CH_3CCl_3 at 277K, as described by Zhang et al. in J. Phys. Chem. 98(16), 4312 (1994); HOMO energy was calculated using MOPAC/PM3, a semi-empirical molecular orbital package; and the number of hydrogen atoms present in the sample was included in the correlation. The results are

reported in Table A under the heading "Estimated Atmospheric Lifetime."

Global Warming Potential

5 Global warming potential (GWP) was determined for the various sample compounds using the above-described calculated values for atmospheric lifetime and experimentally determined infrared absorbance data integrated over the spectral region of interest,
10 typically 500 to 2500 cm^{-1} . The calculations were based on the definition of GWP set forth by the Intergovernmental Panel in Climate Change in Climate Change: The IPCC Scientific Assessment, Cambridge University Press (1990). According to the Panel, GWP
15 is the integrated potential warming due to the release of 1 kilogram of sample compound relative to the warming due to 1 kilogram of CO_2 over a specified integration time horizon (ITH) using the following equation:

$$GWP_{\text{sample}} = \frac{\int_0^{\text{ITH}} \Delta T_{\text{sc}} C_{\text{sc}}^{-1} dt}{\int_0^{\text{ITH}} \Delta T_{\text{CO}_2} C_{\text{CO}_2} dt}$$

25

where ΔT is the calculated change in temperature at the earth's surface due to the presence of a particular compound in the atmosphere [calculated using a spreadsheet model (using parameters described by Fisher
30 et al. in *Nature* 344, 513 (1990)) derived from Atmospheric and Environmental Research, Inc.'s more complete one-dimensional radiative-convective model (described by Wang et al. in *J. Atmos. Sci.* 38, 1167 (1981) and *J. Geophys. Res.* 90, 12971 (1985))], C is the
35 atmospheric concentration of the compound, t is the

atmospheric lifetime of the compound (the calculated value described above), and x designates the compound of interest. Upon integration, the formula is as follows:

- 5 where $A_1 = 0.30036$, $A_2 = 0.34278$, $A_3 = 0.35686$, $\tau_1 = 6.993$, $\tau_2 = 71.108$, and $\tau_3 = 815.73$ in the Siegenthaler (1983) coupled ocean-atmosphere CO₂ model. The results of the calculations are shown in Table A below.

$$GWP_{sample} = \frac{\Delta T C_a x [1 - e^{-\tau x / 100}]}{\Delta T C_{CO_2} (1.3 \times 10^{-10}) [A_1 \tau_1 (1 - e^{-\tau x / 100}) + A_2 \tau_2 (1 - e^{-\tau x / 100}) + A_3 \tau_3 (1 - e^{-\tau x / 100})]}$$

Table A

| Compound | Estimated Atmospheric Lifetime (years) | Atmospheric Lifetime (years) | Global Warming Potential (100 year ITH) |
|--|--|------------------------------|---|
| CF ₃ -CH ₃ | 62.2 | | |
| CF ₃ -O-CH ₃ | 1.6 | | |
| C ₂ F ₅ -CH ₃ | 12.6 | | |
| C ₂ F ₅ -O-CH ₃ | 1.6 | | |
| C ₃ F ₇ -CH ₃ | 9.6 | | |
| C ₃ F ₇ -O-CH ₃ | 1.9 | | |
| C ₄ F ₉ -CH ₃ | 7.0 | | |
| C ₄ F ₉ -O-CH ₃ | 1.9 | 5.5 | 330 |
| C ₄ F ₉ -C ₂ H ₅ | 2.0 | | |
| C ₄ F ₉ -O-C ₂ H ₅ | 0.5 | 1.2 | 70 |
| C ₅ F ₁₁ OCH ₃ | 4.3 | | |
| CF ₃ CF(OCH ₃)CF(CF ₃) ₂ | 4-5 | | |
| C ₅ F ₁₁ OC ₂ H ₅ | -1 | | |
| C-C ₆ F ₁₃ -CH ₃ | 13.7 | | |
| C-C ₆ F ₁₃ -O-CH ₃ | 1.8 | 3.8 | 170 |
| C ₂ F ₅ CF(OCH ₃)CF(CF ₃) ₂ | 4-5 | | |
| CF ₃ CFHCFHCF ₂ CF ₃ | 23+ | | 1000 |

* A. M. Schmoltner et al., J. Phys. Chem. 97, 8976
(1993)

As can be seen in Table A, each of the various
5 alkoxy-substituted perfluorocompounds unexpectedly has
a lower atmospheric lifetime than the corresponding
hydrofluorocarbon, i.e., the hydrofluorocarbon having
the same carbon number. The alkoxy-substituted
perfluorocompounds are thus more environmentally
10 acceptable than the hydrofluorocarbons (which have
previously been proposed as chlorofluorocarbon
replacements).

The chemical stability of the alkoxy-substituted
perfluorocompounds used in the processes and
15 compositions of the invention was also evaluated to
determine their suitability for use in cleaning and
coating applications. In these tests, a compound was
contacted with a chemical agent such as aqueous sodium
acetate, aqueous KOH, concentrated sulfuric acid, or
20 potassium permanganate in acetone to determine the
stability of the compound to base, acid, or oxidant, as
described below:

Stability in the Presence of Base

25 To assess hydrolytic stability, a ten gram
sample of alkoxy-substituted perfluorocompound was
combined with 10 g of 0.1M NaOAc and sealed in a
2.54 cm (internal diameter) by 9.84 cm Monel™ 400
alloy (66% nickel, 31.5% copper, and 1.2% iron and
30 several minor components) tube (available from Paar
Instrument Co. of Moline, Illinois as Part Number
4713cm). The tube was heated at 110°C in a forced air
convection oven for 16 hours. After cooling to room
temperature, a 1 mL sample of the tube contents was
35 diluted with 1 mL of total ionic strength adjustment.

buffer (TISAB, available from Orion Research, Inc., a mixture of 1,2-cyclohexylene dinitrilotetraacetic acid, deionized water, sodium acetate, sodium chloride, and acetic acid). The concentration of fluoride ion

5 (resulting from any reaction of the perfluorocompound with the aqueous NaOAc) was measured using an Orion Model 720A Coulombmeter with a F^- specific electrode which had been previously calibrated using 0.5 and 500 ppm F^- solutions. Based on the measured fluoride

10 ion concentration, the rate at which HF had been generated by reaction of the aqueous NaOAc with the perfluorocompound was calculated. The results are shown below in Table B and indicate that the alkoxy-substituted perfluorocompounds are much more stable to

15 base than is the comparative compound.

Table B

| | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | $C-C_6F_{11}OCH_3$ | $CF_3CFHCFHCF_2CF_3$ |
|--|---------------|-----------------|--------------------|----------------------|
| HF Generation Rate ($\mu g/g/hr$) | 0.67 | 0.22 | 0.33 | 42.9 |

To assess hydrolytic stability under more

20 severely basic conditions, $C_4F_9OCH_3$ (125 g of 99.8% purity, 0.5 mole) was combined with potassium hydroxide (29.4 g, 0.45 mole, dissolved in 26.1 g water) in a 250 mL flask equipped with an overhead stirrer, a condenser, and a thermometer, and the resulting

25 solution was refluxed at $58^\circ C$ for 19 hours. Water (50 mL) was added to the solution after refluxing, and the resulting product was distilled. The lower fluorochemical phase of the resulting distillate was separated from the upper phase and was washed with

30 water (100 mL) to yield 121.3 g of recovered $C_4F_9OCH_3$, which was identical in purity and composition to the

starting material (as shown by gas chromatography). The aqueous base solution remaining in the reaction flask was titrated with standard 1.0 N HCl to reveal that none of the KOH originally charged had been consumed, indicating that the perfluorocompound was stable in the presence of the base.

Stability in the Presence of Acid

To assess hydrolytic stability under acidic conditions, $C_4F_9OCH_3$ (15 g, 0.06 mole) was combined with sulfuric acid (10 g of 96% by weight, 0.097 mole) in a 50 mL flask containing a stir bar and fitted with a reflux condenser. The resulting mixture was stirred for 16 hours at room temperature, and then the resulting upper fluorochemical phase was separated from the resulting lower sulfuric acid phase. Gas-liquid chromatographic (GLC) analysis of the fluorochemical phase revealed the presence of only the starting perfluorocompound and no detectable amount of $C_4F_9CO_2CH_3$, the expected product of hydrolysis. This result (indicating that the perfluorocompound was stable in the presence of the acid) was surprising in view of the discussion by England in J.Org. Chem. 49, 4007 (1984), which states that "[f]luorine atoms attached to carbon which also bears an alkyl ether group are known to be labile to electrophilic reagents. They are readily hydrolyzed in concentrated sulfuric acid, thus providing a route to some esters of fluoroacids."

Stability in the Presence of Oxidant

To assess oxidative stability, potassium permanganate (20 g, 0.126 mole) was dissolved in acetone, and $C_4F_9OCH_3$ (500 g of 99.9% purity, 2.0 mole) was added to the resulting solution. The solution was refluxed for four hours, with no indication that the

permanganate had been consumed (as evidenced by the absence of brown MnO_2). The refluxed solution was then distilled into a 500 mL Barrett trap filled with water. The lower fluorochemical phase of the resulting mixture was separated from the upper phase, was washed with four 1.5 L aliquots of water, and was dried by passage through a column of silica gel to yield 471 g of resulting product. Gas chromatographic analysis of the product revealed no evidence of degradation of the starting perfluorocompound, indicating that the compound was stable in the presence of the oxidant.

Flash Point Testing

The alkoxy-substituted perfluorochemicals
15 $C_4F_9OCH_3$, $C_4F_9OC_2H_5$, and $c-C_6F_{11}OCH_3$ were tested for flash point by the standard method defined by ASTM D3278-89. Each compound was determined to have no flash point.

Examples 1-7 describe the preparation of novel alkoxy-substituted perfluorochemicals of the invention.

Example 1

Preparation of $c-C_6F_{11}CF_2OC_2H_5$

A one liter jacketed round bottom flask was equipped with a reflux condenser, an overhead stirrer, and an addition funnel. The flask was charged with anhydrous dimethyl formamide (300 g) and diethyl sulfate (239 g, 1.55 mole) under a flow of dry nitrogen gas. The resulting stirred solution was cooled to -20°C, and spray-dried potassium fluoride (Aldrich Chemical, which was further dried at 120°C, 67.5 g, 1.16 mole) was added. A mixture of perfluorocyclohexane carbonyl fluoride and isomers of perfluoro methylcyclopentane carbonyl fluoride (approximately 80% purity, 318 g, 0.77 mole) was then

WO 96/23356

PCT/US96/00336

purity. The products of several reactions were combined and distilled (b.=110-120°C). The product identity was confirmed by GCMS and by ^1H and ^{19}F NMR.

5 Example 3


Preparation of 4- CF_3 -c- $\text{C}_6\text{F}_{10}\text{CF}_2\text{OCH}_3$

A one liter round bottom flask was equipped with an overhead stirrer, a condenser, and an addition funnel and was then charged with spray-dried potassium fluoride (Aldrich, which was further dried at 120°C, 15.4 g, 0.26 mole), anhydrous cesium fluoride (6.5 g, 0.043 mole), and anhydrous dimethyl formamide (250 g). A mixture of perfluoro-4-methylcyclohexane carbonyl fluoride and perfluorodimethyl cyclopentane carbonyl fluorides (100 g of 72% purity, 0.189 mole) was then added to the resulting mixture, and the mixture was stirred at ambient temperature for four hours. Dimethyl sulfate (33.3 g, 0.264 mole) was then added to the stirred mixture, and the mixture was further stirred for 72 hours followed by addition of water (500 mL).

The mixture was worked up essentially as described in Example 1 to yield 67 g of a mixture of several components, which was subsequently distilled to give 26.5 g of 4- CF_3 -c- $\text{C}_6\text{F}_{10}\text{CF}_2\text{OCH}_3$ (b.=118-137°C) of 88% purity. The product identity was confirmed by GCMS and by ^1H and ^{19}F NMR, which showed the product to be about 60% of the trans-1,4 isomer and 15% of the cis-1,4 isomer. The product also contained several other isomers of CF_3 -c- $\text{C}_6\text{F}_{10}\text{CF}_2\text{OCH}_3$, resulting from isomers of the perfluoromethylcyclohexane carbonyl fluoride which were present in the starting material.

Example 4


Preparation of



The title compound was prepared essentially as
 5 in Example 3 using anhydrous potassium fluoride (27 g,
 0.46 mole), anhydrous dimethyl formamide (250 g),
 perfluoro-3- piperidinopropionyl fluoride (322 g of
 40.4% purity, 0.32 mole), and dimethyl sulfate (52 g,
 0.41 mole). 275 g of a product mixture of 38% purity
 10 was obtained, which was fractionally distilled to give
 a main fraction of the desired compound (b.=137-139°C,
 91% purity). The product identity was confirmed by
 infrared spectroscopy (IR), GCMS, and ¹H and ¹⁹F NMR.

15 Example 5


Preparation of



The title compound was prepared essentially as
 in Example 3 using anhydrous potassium fluoride (42 g,
 20 0.72 mole), anhydrous dimethyl formamide (300 g),
 perfluoro-2-piperidinoacetyl fluoride (354 g of 47.2%
 purity, 0.46 mole), and diethyl sulfate (94 g,
 0.61 mole). 349 g of a product mixture of 39% purity
 was obtained, which was fractionally distilled to give
 25 a main fraction of the desired compound (b.=135-137°C).
 The product identity was confirmed by IR, GCMS, and ¹H
 and ¹⁹F NMR.

Example 6

Preparation of



The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (17.7 g, 0.30 mole), anhydrous dimethyl formamide (300 g), perfluoro-3-morpholinopropionyl fluoride (890 g of 8.6% purity, 0.2 mole), and dimethyl sulfate (37 g, 0.29 mole). 88 g of a product mixture of 57% purity was obtained, which was fractionally distilled to give a main fraction of the desired compound (b.p.=129°C, 90% purity). The product identity was confirmed by IR, GCMS, and ¹H and ¹⁹F NMR.

15 Example 7Preparation of CH₃OCF₂-c-C₆F₁₀CF₂OCH₃

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (6.62 g, 0.011 mole), anhydrous dimethyl formamide (200 g), FCO-c-C₆F₁₀COF (253 g of approximately 26% purity, 0.185 mole; the remainder of the material comprised a mixture of mono-functional, non-functional, and isomeric compounds), and dimethyl sulfate (14.4 g, 0.011 mole). 21 g of solid CH₃OCF₂-c-C₆F₁₀CF₂OCH₃ was obtained (product identity confirmed by IR and ¹H and ¹⁹F NMR).

Examples 8-28 describe the use of alkoxy-substituted perfluorocompounds in various different cleaning applications according to the cleaning process of the invention.

5

A number of different alkoxy-substituted perfluorocompounds were prepared for use in cleaning, as described below:

10 Preparation of $C_4F_9OC_2H_5$

A 20 gallon Hastalloy C reactor, equipped with a stirrer and a cooling system, was charged with spray-dried potassium fluoride (7.0 kg, 120.3 mole). The reactor was sealed, and the pressure inside the reactor was reduced to less than 100 torr. Anhydrous dimethyl formamide (22.5 kg) was then added to the reactor, and the reactor was cooled to below 0°C with constant agitation. Heptafluorobutyryl fluoride (22.5 kg of 58% purity, 60.6 mole) was added to the reactor contents. When the temperature of the reactor reached -20°C, diethyl sulfate (18.6 kg, 120.8 mole) was added to the reactor over a period of approximately two hours. The resulting mixture was then held for 16 hours with continued agitation, was raised to 50°C for an additional four hours to facilitate complete reaction, and was cooled to 20°C. Then, volatile material (primarily perfluorooxacyclopentane present in the starting heptafluorobutyryl fluoride) was vented from the reactor over a three-hour period. The reactor was then resealed, and water (6.0 kg) was added slowly to the reactor. After the exothermic reaction of the water with unreacted perfluorobutyryl fluoride subsided, the reactor was cooled to 25°C, and the reactor contents were stirred for 30 minutes. The

reactor pressure was carefully vented, and the lower organic phase of the resulting product was removed to afford 17.3 kg of material which was 73% $C_4F_7OCH_3$ (b.p. = $-75^\circ C$). The product identity was confirmed by GCMS and by 1H and ^{19}F NMR.

Preparation of $C_4F_7OCH_3$

The reaction was carried out in the same equipment and in a similar manner to the procedure of Example 7 above, but using the following materials: spray-dried potassium fluoride (6 kg, 103.1 mole), anhydrous dimethyl formamide (25.1 kg), perfluorobutyryl fluoride (58% purity, 25.1 kg, 67.3 mole), and dimethyl sulfate (12.0 kg, 95.1 mole). 22.6 kg of product was obtained, which was 63.2% $C_4F_7OCH_3$ (b.p. = -58 – $-60^\circ C$). The product identity was confirmed by GCMS and by 1H and ^{19}F NMR.

Preparation of $c-C_6F_{11}OCH_3$

A 500 ml, 3-necked round bottom flask equipped with an overhead stirrer, an addition funnel, and a condenser was charged with anhydrous cesium fluoride (27.4 g, 0.18 mole), anhydrous diethylene glycol dimethyl ether (258 g, hereinafter diglyme), and dimethyl sulfate (22.7 g, 0.18 mole). Perfluorocyclohexanone (50g, 0.18 mole) was then added dropwise to the resulting stirred mixture, and stirring was continued for 18 hours after the addition. Water (approximately 200 ml) was added to the resulting mixture, and the lower fluorochemical phase of the mixture was separated from the upper phase and washed once with saturated aqueous sodium chloride solution. Since the fluorochemical phase still contained about 12% diglyme, water was added to it, and the resulting product was azeotropically distilled to yield 32.8 g of

$\text{C-C}_6\text{F}_{11}\text{OCH}_3$ (b.p.=100°C), which was free of diglyme. The product identity was confirmed by IR, GCMS, and ^1H and ^{19}F NMR.

5 Preparation of $(\text{CF}_3)_2\text{CFCF}_2\text{OCH}_3$

The title compound was prepared essentially as in Example 1 using anhydrous potassium fluoride (31.9 g, 0.55 mole), anhydrous dimethyl formamide (186 g), perfluoroisobutryl fluoride (108 g of 99% purity, 0.5 mole), and dimethyl sulfate (81.9 g, 0.65 mole). The resulting mixture was held at -20°C for 16 hours, was warmed to 40°C for 3.5 hours, and was then distilled to yield 109 g of the title compound (83.6% purity by GLC; also containing 11.6% $(\text{CF}_3)_2\text{CFCOF}$). The reaction mixtures from several runs were combined and distilled (b.=60-61°C).

Preparation of $(\text{CF}_3)_2\text{CFCF}_2\text{OC}_2\text{H}_5$

The title compound was prepared essentially as in Example 1 using anhydrous potassium fluoride (31.9 g, 0.55 mole), anhydrous dimethyl formamide (184 g), perfluoroisobutryl fluoride (112.3 g of 77% purity, 0.4 mole), and diethyl sulfate (100.1 g, 0.65 mole). The resulting mixture was worked up essentially as in Example 3 to yield 80 g of the title compound. The product identity was confirmed by IR, GCMS, and ^1H and ^{19}F NMR.

Preparation of $\text{C}_6\text{F}_{11}\text{OCH}_3$

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (6.62 g, 0.011 mole), anhydrous dimethyl formamide (800 g), $\text{C}_6\text{F}_{11}\text{COF}$ (456.7 g, 1.09 mole), and dimethyl sulfate (14.4 g, 0.011 mole). The resulting mixture was worked up essentially as in Example 3 to give 444 g

WO 96/22356

PCT/US96/00336

of the title compound (99.7% purity, b.=142-144°C). The product identity was confirmed by IR, GCMS, and ^1H and ^{19}F NMR.

5 Preparation of $\text{C}_2\text{F}_5\text{CF}(\text{OCH}_3)\text{CF}(\text{CF}_3)_2$

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (7.2 g, 0.123 mol), anhydrous diethylene glycol dimethyl ether (diglyme, 60 g), methyltrialkyl ($\text{C}_8\text{-C}_{10}$) ammonium chloride (AdogenTM 464, available from Aldrich Chemical Company, 1.8 g), $\text{C}_2\text{F}_5\text{COCF}(\text{CF}_3)_2$ (30 g, 0.095 mol, prepared by the reaction of pentafluoropropionyl fluoride with KF and hexafluoropropene), and dimethyl sulfate (15.5 g, 0.123 mol). The reaction mixture was stirred at room temperature for 72 hours. Approximately 100 mL of 10% aqueous potassium hydroxide was then added to the reaction mixture, and the resulting product was azeotropically distilled from the mixture. The lower phase of the resulting distillate was separated from the upper phase, was washed with water, and was distilled to give 26.7 g of product ether (boiling range 90-92°C; >99% purity by gas-liquid chromatography (GLC)). The product identity was confirmed by GCMS and ^1H and ^{19}F NMR.

Preparation of $\text{C}_3\text{F}_7\text{OCH}_3$

A jacketed one liter round bottom flask was equipped with an overhead stirrer, a solid carbon dioxide/acetone condenser, and an addition funnel. The flask was charged with spray-dried potassium fluoride (85 g, 1.46 mol) and anhydrous diethylene glycol dimethyl ether (375 g) and was then cooled to about -20°C using a recirculating refrigeration system. $\text{C}_2\text{F}_5\text{COF}$ (196 g, 1.18 mol) was added to the flask over a

period of about one hour. The flask was then warmed to about 24°C, and dimethyl sulfate (184.3 g, 1.46 mol) was then added dropwise via the addition funnel over a 45 minute period. The resulting mixture was then
5 stirred at room temperature overnight. Water (a total of 318 mL) was then added dropwise to the mixture. The mixture was transferred to a one liter round bottom flask, and the resulting product ether was azeotropically distilled. The lower product phase of
10 the resulting distillate was separated from the upper aqueous phase, was washed once with cold water, and was subsequently distilled to give 180 g of product (b.p. 36°C; >99.9% purity by GLC). The product identity was confirmed by GCMS and by ¹H and ¹⁹F NMR.

15

Preparation of CF₃CF(OCH₃)CF(CF₃)₂

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (12.8 g, 0.22 mol), anhydrous diethylene glycol
20 dimethyl ether (diglyme, 106 g), methyltrialkyl(C₈-C₁₀) ammonium chloride (Adogen™ 464, available from Aldrich Chemical Company, 4 g), CF₃COCF(CF₃)₂ (53.2 g, 0.20 mol, prepared essentially by the procedure of Smith et al., J. Am. Chem. Soc., 84,
25 4285 (1962)), and dimethyl sulfate (33.9 g, 0.72 mol). Aqueous potassium hydroxide was added to the reaction mixture (approximately 25 g of 50% solution), followed by water (200 mL). The resulting crude product was azeotropically distilled from the reaction mixture.
30 The lower phase of the resulting distillate was separated from the upper phase, was washed with water, was dried over anhydrous sodium sulfate, and was distilled (b.p. 82-83°C; yield of 45 g). The product identity was confirmed by GCMS and by FTIR.

35

Preparation of $C_8F_{11}OCH_3$

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (32 g, 0.55 mol), anhydrous diethylene glycol dimethyl ether (diglyme, 375 g), methyltrialkyl(C_8 - C_{10}) ammonium chloride (Adogen™ 464, available from Aldrich Chemical Company, 12.5 g), C_8F_9COF (218 g of 60.7% purity, 0.5 mol), and dimethyl sulfate (69.3 g, 0.55 mol). The reaction mixture was stirred at room temperature overnight. Approximately 100 mL of 10% aqueous potassium hydroxide was then added to the mixture, and the resulting product was azeotropically distilled from the mixture. The lower phase of the resulting distillate was separated from the upper phase, was washed with water, was treated with aqueous potassium hydroxide solution (53 g of 50%), and was then refluxed for one hour. A second azeotropic distillation and water washing yielded crude product which was further purified by distillation through a ten-plate perforated column to provide the product ether (boiling range 82-84°C; 96.2% purity by GLC). The product identity was confirmed by GCMS and by 1H and ^{19}F NMR.

Preparation of $C_8F_{11}OC_2H_5$

The title compound was prepared essentially as in Example 3 using anhydrous potassium fluoride (38.6 g, 0.67 mol), anhydrous diethylene glycol dimethyl ether (diglyme, 500 g), methyltrialkyl(C_8 - C_{10}) ammonium chloride (Adogen™ 464, available from Aldrich Chemical Company, 10.5 g), C_8F_9COF (260 g of 60.7% purity, 0.59 mol), and diethyl sulfate (102.4 g, 0.67 mol). The reaction mixture was stirred at room temperature overnight, and then the resulting product was azeotropically distilled from the reaction mixture. The lower product phase of the

resulting distillate was separated from the upper phase and was treated with approximately 50 g of 50% aqueous potassium hydroxide, was refluxed for four hours, and was stirred at room temperature overnight. A second
5 azeotropic distillation and water washing gave crude product which was further purified by distillation through a ten-plate perforated column to provide the product ether (boiling point 96°C; 99.6% purity by GLC). The product identity was confirmed by GCMS and by ¹H and
10 ¹⁹F NMR.

Solvency Properties

A number of potential solvents were tested for their ability to dissolve hydrocarbons of increasing
15 molecular weight according to the procedure described in U.S. Patent No. 5,275,669 (Van Der Puy et al.). The data shown in Table 1 were obtained by determining the largest normal hydrocarbon alkane which was soluble in a particular solvent at a level of 50 percent by
20 volume. The numbers in the Table correspond with the carbon number of the largest alkane, e.g., "8" refers to octane. Measurements were made from room temperature up to the boiling point of the solvent. For comparative purposes, hydrofluorocarbons (HFCs) and
25 perfluorocarbons (PFCs) were also tested using this method.







Table 1

| Temperature (°C) | C ₄ F ₉ OCH ₃ | C ₄ F ₉ OC ₂ H ₅ | c-C ₆ F ₁₁ OCH ₃ | CF ₃ CFHCFHCFHCF ₃ | C ₆ F ₁₄ | C ₈ F ₁₈ | C ₉ F ₁₁ H | C ₈ F ₁₃ H |
|---------------------|--|--|---|--|--------------------------------|--------------------------------|----------------------------------|----------------------------------|
| 23 | 9 | 12 | 10 | 7 | 6 | 5 | 7 | 7 |
| 30 | 10 | 12 | 11 | 7 | | | | |
| 40 | 10 | 13 | 11 | 8 | 6 | 6 | 8 | 8 |
| 50 | 12 | 14 | 13 | 8 | 7 | 6 | | 8 |
| 55 | 12 | 15 | 13 | 9 | | | | |
| 60 | 12 | 15 | 13 | | 7 | 7 | | 9 |
| 73 | | 17 | 15 | | | 7 | | 10 |
| 101 | | | 18 | | | 9 | | |

The data in Table 1 show that hydrocarbon alkanes are significantly more soluble in the alkoxy-substituted perfluorocompounds used in the cleaning process of this invention than in the comparative compounds, the HFCs and PFCs. This improved solvency was more pronounced at elevated temperatures. Thus, the cleaning process of the invention can be used to remove higher molecular weight hydrocarbons (e.g., oils and greases) from substrate surfaces than can be removed using HFCs or PFCs. The higher solvency of the alkoxy-substituted perfluorocompounds for hydrocarbon alkanes indicates that these perfluorocompounds can serve not only as superior cleaning solvents for removing hydrocarbon soils, but can also be effective as solvents for depositing hydrocarbon coatings, e.g., coatings of lubricant, onto substrate surfaces.

Using essentially the above-described method, the solvency properties of other alkoxy-substituted perfluorocompounds were tested at room temperature. The compounds tested and the results obtained are shown in Table 2 below.

Table 2

| Compound | Largest Soluble |
|---|-----------------|
|  | 9 |
|  | 11 |
| $C_9F_{17}OCH_3$ | 6 |
| $(CF_3)_2CF CF_2OCH_3$ | 9 |
| $C_2F_5CF(OCH_3)CF(CF_3)_2$ | 8 |
| $CF_3CF(OCH_3)CF(CF_3)_2$ | 9 |
| $C_3F_7OCH_3$ | 10 |
| $C_5F_{11}OCH_3$ | 8 |
| $C_5F_{11}OC_2H_5$ | 10 |
|  | 8 |
|  | 7 |
|  | 9 |
|  | 8 |

Examples 8-10 and Comparative Examples A-C

- In the following Examples and Comparative
- 5 Examples, the cleaning ability of the alkoxy-substituted perfluorocompounds used in the cleaning process of the invention was further evaluated. A 1.28 cm x 1.28 cm x 0.225 cm wire-wrapped, aluminum coupon was coated with white heavy mineral oil

(available from Aldrich Chemical) by immersing the coupon in an oil-filled beaker. The initial amount of the oil on the coupon was determined by weighing it on an analytical balance to the nearest 0.1 mg. The coupon was immersed in a container of solvent and sonicated for 1 minute at the indicated temperature (see Table 3 below for the solvents and temperatures used). The coupon was then weighed again, and the results were recorded in Table 3 as percent oil removal.

Table 3

| Example | 8 | 9 | 10 | Comparative A | Comparative B | Comparative C |
|---------------|---------------|-----------------|--------------------|---------------|---------------|----------------|
| Temp. (°C) | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | $C-C_6F_{11}OCH_3$ | C_6F_{14} | $C_6F_{13}H$ | $CF_2ClCFCl_2$ |
| 23 | 60.3 | 56.0 | 74.4 | 54.9 | 71.7 | 98.9 |
| 50 | 98.7 | 99.2 | 96.5 | 67.6 | 86.8 | 98.7 |
| 60 | 99.9 | 100.0 | 99.8 | | | |

The data in Table 3 show that the alkoxy-substituted perfluorocompounds removed amounts of the mineral oil which were comparable to the amounts removed by the comparative PFC and HFC compounds at room temperature. At elevated temperature, the cleaning properties of the perfluorocompounds were superior to those of the PFC and HFC compounds and equivalent to those of the comparative CFC compound.

10 Examples 11-13

Using essentially the same procedure as that described in Examples 8-10, the ability of the alkoxy-substituted perfluorocompounds to remove a fluorinated oil was evaluated. As in the previous Examples, a coupon was immersed in KrytoxTM 157FSM perfluoropolyether oil having carboxylic acid end groups (available from DuPont), and the percent oil remaining after immersion in the solvent (at room temperature) was determined. The results are shown in Table 4 below.

Table 4

| Example | 11 | 12 | 13 |
|-----------|---------------|-----------------|--------------------|
| Compound | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | $C-C_6F_{11}OCH_3$ |
| % Removed | 99.1 | 99.3 | 96.5 |

25 The data show that the alkoxy-substituted perfluorocompounds very effectively removed the perfluoropolyether oil from the surface of the coupon. This indicates that the perfluorocompounds can function well as cleaning solvents for the removal of halogenated compounds such as halogenated oils and greases.

Examples 14-16 and Comparative Examples D-E

The ability of alkoxy-substituted perfluorocompounds to function as a rinse agent in a co-solvent cleaning process was evaluated. The above-described aluminum coupon was coated with solder flux (available from Alpha Metals as Alpha 611 rosin, mildly activated flux) by immersing the coupon into a flux-filled beaker. The flux-coated coupon was then dried using a forced air convection drier. The initial amount of the flux on the coupon was determined by weighing it on an analytical balance to the nearest 0.1 mg. The coupon was immersed in a container of a mixed solvating agent comprising approximately 50% methyl decanoate and 50% dipropylene glycol di-n-butyl ether and was sonicated for 1 minute at approximately 55°C. The coupon was then immersed for 30 seconds into alkoxy-substituted perfluorocompound which had been heated to its boiling point. The coupon was weighed again, and the results were recorded in Table 5 below as percent oil removed from the coupon.

Table 5

| Example | 14 | 15 | 16 | Comparative D | Comparative E |
|--------------|---------------|-----------------|--------------------|------------------|------------------|
| Compound | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | $C-C_6F_{11}OCH_3$ | C_6F_{14} | $C_6F_{13}H$ |
| % Removed | 100.0 | 100.0 | 100.0 | 51.9 | 91.2 |

The data in Table 5 show that the alkoxy-substituted perfluorocompounds (used according to the cleaning process of the invention) effectively removed the solvating agent and flux residues, showing solvency properties superior to those of the comparative PFC and HFC compounds.

Examples 17-18 and Comparative Example F

The above-described aluminum coupon was dipped into Brayco 8152 perfluoropolyether oil (available from Castrol Inc., molecular weight of about 10,000) and then immersed in alkoxy-substituted perfluorocompound vapor (over the boiling liquid) for 60 seconds. The percent oil removal was determined in the above-described manner. The results are shown in Table 6.

10

Table 6

| | 17 | 18 | Comparative F |
|----------------------|---------------|-----------------|---------------|
| Compound | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | C_6F_{14} |
| Percent Soil Removed | 89.9% | 93.3% | 92.9% |

Examples 19-20 and Comparative Example G

15

The above-described test coupon was dipped into a paraffinic oil comprising a mixture of linear and branched hydrocarbons (DuoSeal Pump Oil, available from Sargent Welch), was immersed in mixed solvating agent comprising approximately 50% methyl caproate and 50% dipropylene glycol di-n-butyl ether for 30 seconds, and was then rinsed in boiling alkoxy-substituted perfluorocompound for 30 seconds. The percent oil removal was determined in the above-described manner. The results are shown in Table 7.

25

Table 7

| | 19 | 20 | Comparative G |
|----------------------|---------------|-----------------|---------------|
| Compound | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | C_6F_{14} |
| Percent Soil Removed | 99.8% | 100.0% | 89.2% |

Examples 21-22

The above-described test coupon was dipped in white heavy mineral oil (available from Aldrich Chemical), was immersed in a boiling single-phase mixture of 40 volume % of a solvating agent comprising essentially methyl decanoate and 60 volume % of alkoxy-substituted perfluorocompound (a cleaning composition of the invention) for 60 seconds, was cooled for 60 seconds, and was then immersed in mixture vapor for 30 seconds. The percent oil removal was determined in the above-described manner. The results are shown in Table 8.

Table 8

| | 21 | 22 |
|---|---------------|-----------------|
| Fluorinated Component of Cleaning Composition | $C_7F_9OCH_3$ | $C_8F_9OC_2H_5$ |
| Percent Soil Removed | 94.61% | 94.28% |

Examples 23-24 and Comparative Example H

The above-described test coupon was dipped into DuoSeal Pump Oil (available from Sargent-Welch), was immersed in a boiling mixture of 40 volume % of a solvating agent comprising mixed terpenes having a boiling range of 243-274°C and 60 volume % of alkoxy-substituted perfluorocompound (a cleaning composition of the invention), was cooled for 60 seconds, and was then immersed in mixture vapor for 30 seconds. The percent oil removal was determined in the above-described manner. The results are shown in Table 9.

Table 9

| | 23 | 24 | Comparative H |
|---|---------------|-----------------|---------------|
| Fluorinated Component of Cleaning Composition | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | C_6F_{14} |
| Percent Soil Removed | 86.4% | 99.4% | 75.7% |

Examples 25-26 and Comparative Example I

- 5 The above-described test coupon was dipped into DuoSeal Pump Oil (available from Sargent-Welch) and was then immersed in a mixture of 40 volume % $n-C_6H_{14}$ and 60 volume % alkoxy-substituted perfluorocompound (a cleaning composition of the invention) for 60 seconds
- 10 at room temperature with ultrasonic agitation. The percent oil removal was determined in the above-described manner. The results are shown in Table 10.

Table 10

| | 25 | 26 | Comparative I |
|---|---------------|-----------------|---------------|
| Fluorinated Component of Cleaning Composition | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | C_6F_{14} |
| Percent Soil Removed | 92.5% | 99.0% | 88.5% |

15

Examples 27-28 and Comparative Example J

- 20 The above-described test coupon was dipped into DuoSeal Pump Oil (available from Sargent-Welch) and was then immersed in the vapor of a boiling mixture of 40 volume % $n-C_6H_{14}$ and 60 volume % alkoxy-substituted perfluorocompound (a cleaning composition of the invention) for 60 seconds. The percent oil removal was determined in the above-described manner. The results
- 25 are shown in Table 11.

Table 11

| Example | 27 | 28 | Comparative J |
|---|---------------|-----------------|---------------|
| Fluorinated Component of Cleaning Composition | $C_4F_9OCH_3$ | $C_4F_9OC_2H_5$ | C_6F_{14} |
| Percent Soil Removed | 90.8% | 97.1% | 73.8% |

5 The results obtained in Examples 17-28 show that alkoxy-substituted perfluorocompounds are effective at removing a variety of contaminants from substrate surfaces.

10 Examples 29-38 describe the preparation of coating compositions of the invention and the evaluation of alkoxy-substituted perfluorocompounds for use according to the coating process of the invention.

15 Examples 29-31

 The ability of alkoxy-substituted perfluorocompounds to dissolve several halogenated oils was determined by adding a measured amount of oil to alkoxy-substituted perfluorocompound until the

20 resulting mixture became turbid or phase-split. Miscibility was defined as greater than or equal to 50 percent by volume solubility at room temperature. The results (shown in Table 12) indicate that alkoxy-

25 substituted perfluorocompounds have very high ability to dissolve halogenated oils. Thus, the perfluorocompounds can be used as carrier solvents for halogenated oils in the deposition of coatings of such oils on substrate surfaces.

Table 12

| Example | 29 | 30 | 31 |
|--|--|--|---|
| Compound | C ₂ F ₅ OCH ₃ | C ₂ F ₅ OC ₂ H ₅ | c-C ₆ F ₁₁ OCH ₃ |
| Solute | | | |
| Brayco 815Z Perfluoropolyeth er (MW about 10,000) | Miscible | Miscible | Miscible |
| Fomblin™ AM-2001 Functionalized Perfluoropolyeth er (available from Ausimont Inc.) | Miscible | Miscible | Miscible |
| Chlorotrifluoro ethylene Fluid (available from Inland as Inland 41 Vacuum Pump Oil) | Miscible | Miscible | Miscible |

Examples 32-38 and Comparative Examples K-L

- 5 To demonstrate the use of alkoxy-substituted perfluorocompounds as dispersing agents, a series of polytetrafluoroethylene (PTFE) dispersions were prepared and evaluated. Commercially, PTFE is available from DuPont as Teflon™ powder or as Vydax™
- 10 dispersions in either water or isopropanol (IPA) (20-30 weight %). To prepare useful coatings, these concentrated dispersions must be further diluted with a co-dispersant to 1-10 weight %, more frequently 1-3 weight %.
- 15 Although the commercial PTFE dispersions may be further diluted with either water or isopropanol, these fluids are often not preferred due to performance and/or safety reasons.

- In the following Examples 32-38, the commercially-available, concentrated dispersions were
- 20 diluted at room temperature with alkoxy-substituted perfluorocompound or with a comparative compound (perfluoro-N-methyl morpholine) to produce a dilute

dispersion of approximately 1.5 weight %. The resulting dispersions were then evaluated as to homogeneity and assigned one of the ratings shown in Table 13 below. A description of the dispersions prepared and the results obtained are shown in Table 14.

Table 13

| Rating | Rating Description |
|-----------|--|
| Poor | Agglomerated PTFE--not useful. |
| Fair | Some agglomeration; extensive grainy or waxy coating on the surface of glass vial. |
| Good | Homogeneous dispersion; some grainy coating on glass vial. |
| Very Good | Homogeneous dispersion; little to no grainy coating on glass vial. |

10

Table 14

| Example No. | Product | Dispersant | Final Dispersion Weight % | Rating |
|---------------|--------------------|--|---------------------------|--------------|
| 32 | Vydax™ AR/IPA | C ₄ F ₉ OCH ₃ | 1.49 | Very Good |
| 33 | Vydax™ HD/IPA | C ₄ F ₉ OCH ₃ | 1.52 | Very Good |
| 34 | Teflon™ MP1100/IPA | C ₄ F ₉ OCH ₃ | 1.59 | Very Good |
| 35 | Teflon™ MP1100/IPA | C ₄ F ₉ OCH ₂ CH ₃ | 1.52 | Very Good |
| 36 | Vydax™ ARW/Water | C ₄ F ₉ OCH ₃ | 0.92 | Fair to Good |
| 37 | Vydax™ ARW/Water | C ₄ F ₉ OCH ₂ CH ₃ | 0.91 | Fair to Good |
| 38 | Vydax™ ARW/Water | C ₄ F ₉ OCH ₂ CH ₃ | 1.49 | Fair to Good |
| Comparative K | Vydax™ AR/IPA | Perfluoro-N-methyl morpholine | 1.50 | Poor |
| Comparative L | Vydax™ ARW/Water | Perfluoro-N-methyl morpholine | 1.50 | Poor |

15

The data show that alkoxy-substituted perfluorocompounds can be used to prepare homogeneous

dispersions of PTFE, whereas the comparative PFC compound cannot. Thus, the perfluorocompounds can be used as carrier solvents for PTFE in the deposition of coatings of PTFE on substrate surfaces.

5

Examples 39-44 describe the use of alkoxy-substituted perfluorocompounds in water removal (drying) according to the cleaning process of the invention.

10 Examples 39-44

A series of water displacement compositions was prepared and evaluated. The compositions comprised alkoxy-substituted perfluorocompound and either a surface active agent ($C_4F_9OC_2F_5OCF_3CONHC_2H_4OH$, described
15 in U.S. Patent Nos. 5,125,978 and 5,089,152 (Flynn et al.)) or a co-solvent. The compositions (and the results obtained) are shown in Table 15 below.

The following procedure was utilized: an 11.7 mm O.D. by 32 mm glass vial was wetted with
20 deionized water. The wetted vial was placed in a vessel containing a water displacement composition which had been heated to its boiling point. A saturated zone of alkoxy-substituted perfluorocompound (and cosolvent, if any) vapor was maintained above the
25 boiling composition. The vial was agitated by ultrasound for 1 minute while dislodging and displacing any adhering water. The vial was then removed from the boiling composition and held in the saturated vapor zone for 30-60 seconds to allow drainage of excess
30 water displacement composition back into the vessel and thereby minimize fluid carryout. The vial was then visually inspected for the presence of residual water. The results are shown in Table 15 below, where a "+"

indicates that 75% of the water was removed from the vial in 60 seconds.

Table 15

| Ex. No. | Alkoxy-substituted Perfluorocompound | Co-solvent (5 Volume %) | Concentration of Surface Active Agent (weight %) | Water Removal |
|---------|--------------------------------------|-------------------------|--|---------------|
| 39 | $C_4F_9OCH_3$ | None | 0.2 | + |
| 40 | $C_4F_9OC_2H_5$ | None | 0.2 | + |
| 41 | $C_4F_9OCH_3$ | CH_3OH | None | + |
| 42 | $C_4F_9OCH_3$ | $(CH_3)_2CHOH$ | None | + |
| 43 | $C_4F_9OC_2H_5$ | CH_3OH | None | + |
| 44 | $C_4F_9OC_2H_5$ | $(CH_3)_2CHOH$ | None | + |

5

The results in Table 15 show that alkoxy-substituted perfluorocompounds are effective in removing water from substrate surfaces.

10




Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention.

We claim:

1. A process for removing contaminants from the surface of a substrate comprising the step of
 5 contacting a substrate with a liquid- and/or vapor-phase cleaning composition comprising at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane,
 perfluorocycloalkyl-containing perfluoroalkane, or
 10 perfluorocycloalkylene-containing perfluoroalkane compound, said compound optionally containing one or more additional catenary heteroatoms.

2. A process for removing contaminants from the
 15 surface of a substrate comprising the step of contacting a substrate with a liquid- and/or vapor-phase cleaning composition comprising at least one compound selected from the group consisting of $\text{C-C}_6\text{F}_{11}\text{CF}_2\text{OC}_2\text{H}_5$, $\text{C-C}_6\text{F}_{11}\text{CF}_2\text{OCH}_3$, $4\text{-CF}_3\text{-C-C}_6\text{F}_{10}\text{CF}_2\text{OCH}_3$,





20



25 $\text{CH}_3\text{OCF}_2\text{-C-C}_6\text{F}_{10}\text{CF}_2\text{OCH}_3$, $\text{C}_6\text{F}_5\text{OC}_2\text{H}_5$, $\text{C}_6\text{F}_5\text{OCH}_3$, $\text{C-C}_6\text{F}_{11}\text{OCH}_3$, $(\text{CF}_3)_2\text{CFCF}_2\text{OCH}_3$, $(\text{CF}_3)_2\text{CFCF}_2\text{OC}_2\text{H}_5$, $\text{C}_6\text{F}_{17}\text{OCH}_3$, $\text{C}_2\text{F}_5\text{CF}(\text{OCH}_3)\text{CF}(\text{CF}_3)_2$, $\text{CF}_3\text{CF}(\text{OCH}_3)\text{CF}(\text{CF}_3)_2$, $\text{C}_3\text{F}_{11}\text{OCH}_3$, $\text{C}_3\text{F}_{11}\text{OC}_2\text{H}_5$, and $\text{C}_3\text{F}_7\text{OCH}_3$.

3. A cleaning composition comprising (a) a major amount of at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound, said compound optionally containing one or more additional catenary heteroatoms; and (b) a minor amount of at least one co-solvent selected from the group consisting of alcohols, ethers, alkanes, alkenes, perfluorocarbons, perfluorinated tertiary amines, perfluoroethers, cycloalkanes, esters, ketones, aromatics, siloxanes, hydrochlorocarbons, hydrochlorofluorocarbons, and hydrofluorocarbons.

4. A cleaning composition comprising (a) a major amount of at least one compound selected from the group consisting of $c-C_6F_{11}CF_2OC_2H_5$, $c-C_6F_{11}CF_2OCH_3$, $4-CF_3-c-C_6F_{10}CF_2OCH_3$,






25 $C_5F_{11}OCH_3$, $C_5F_{11}OC_2H_5$, and $C_3F_7OCH_3$; and (b) a minor amount of at least one co-solvent selected from the group consisting of alcohols, ethers, alkanes, alkenes, perfluorocarbons, perfluorinated tertiary amines,

perfluoroethers, cycloalkanes, esters, ketones, aromatics, siloxanes, hydrochlorocarbons, hydrochlorofluorocarbons, and hydrofluorocarbons.

- 5 5. A process for depositing a coating on a substrate surface comprising the step of applying to at least a portion of at least one surface of a substrate a coating of a liquid coating composition comprising
- 10 (a) a solvent composition comprising at least one mono-, di-, or trialkoxy-substituted perfluoroalkane, perfluorocycloalkane, perfluorocycloalkyl-containing perfluoroalkane, or perfluorocycloalkylene-containing perfluoroalkane compound, said compound optionally
- 15 containing one or more additional catenary heteroatoms; and (b) at least one coating material which is soluble or dispersible in said solvent composition.

- 20 6. A process for depositing a coating on a substrate surface comprising the step of applying to at least a portion of at least one surface of a substrate a coating of a liquid coating composition comprising
- (a) a solvent composition comprising at least one compound selected from the group consisting of
- C-C₆F₁₁CF₂OC₂H₅, C-C₆F₁₁CF₂OCH₃, 4-CF₃-C-C₆F₁₀CF₂OCH₃,




25



$C_4F_9OCH_3$, $C-C_6F_{11}OCH_3$, $(CF_3)_2CFCH_2OCH_3$, $(CF_3)_2CFCH_2OC_2H_5$,
 $C_8F_{17}OCH_3$, $C_2F_5CF(OCH_3)CF(CF_3)_2$, $CF_3CF(OCH_3)CF(CF_3)_2$,
 $C_8F_{11}OCH_3$, $C_8F_{11}OC_2H_5$, and $C_3F_7OCH_3$; and (b) at least one
 5 said solvent composition.

7. A coating composition comprising (a)
 (a) a solvent composition comprising at least one
 mono-, di-, or trialkoxy-substituted perfluoroalkane,
 10 perfluorocycloalkane, perfluorocycloalkyl-containing
 perfluoroalkane, or perfluorocycloalkylene-containing
 perfluoroalkane compound, said compound optionally
 containing one or more additional catenary heteroatoms;
 and (b) at least one coating material which is soluble
 15 or dispersible in said solvent composition.

8. A coating composition comprising (a)
 (a) a solvent composition comprising at least one
 compound selected from the group consisting of
 20 $C-C_6F_{11}CF_2OC_2H_5$, $C-C_6F_{11}CF_2OCH_3$, $4-CF_3-C-C_6F_{10}CF_2OCH_3$,



25 $CH_3OCF_2-C-C_6F_{10}CF_2OCH_3$, $C_4F_9OC_2H_5$,
 $C_4F_9OCH_3$, $C-C_6F_{11}OCH_3$, $(CF_3)_2CFCH_2OCH_3$, $(CF_3)_2CFCH_2OC_2H_5$,
 $C_8F_{17}OCH_3$, $C_2F_5CF(OCH_3)CF(CF_3)_2$, $CF_3CF(OCH_3)CF(CF_3)_2$,
 $C_8F_{11}OCH_3$, $C_8F_{11}OC_2H_5$, and $C_3F_7OCH_3$; and (b) at least one

coating material which is soluble or dispersible in said solvent composition.

9. Alkoxy-substituted perfluorocompounds
5 represented by the general formula



- wherein R_f^1 and R_f^2 are both substituted or unsubstituted
10 perfluoroalkyl groups having from 1 to about 6 carbon atoms or are both substituted or unsubstituted perfluoroalkylene groups having from 2 to about 4 carbon atoms, said perfluoroalkylene groups being bonded to one another to form a ring; y is an integer
15 of 1 to about 8; C_yF_{2y} is linear or branched; and R_n is selected from the group consisting of linear or branched alkyl groups having from 1 to about 8 carbon atoms, cycloalkyl-containing alkyl groups having from 4 to about 8 carbon atoms, and cycloalkyl groups having
20 from 3 to about 8 carbon atoms; wherein the groups R_f^1 , R_f^2 , and R_n can independently contain one or more catenary heteroatoms.

10. Alkoxy-substituted perfluorocompounds
25 represented by the general formula



- wherein R_f^3 is a substituted or unsubstituted
30 perfluorocycloalkyl, perfluorocycloalkanediyl, or perfluorocycloalkanetriyl group having from 3 to about 12 carbon atoms; each R_n is independently selected from the group consisting of linear or branched alkyl groups having from 1 to about 8 carbon atoms, cycloalkyl-

containing alkyl groups having from 4 to about 8 carbon atoms, and cycloalkyl groups having from 3 to about 8 carbon atoms; and x' is an integer of 1 to 3, wherein either or both of the groups R_2' and R_n can contain one or more catenary heteroatoms.

INTERNATIONAL SEARCH REPORT

 Later national Application No
 PCT/US 96/00336

 CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C11D7/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 C11D C07D C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|----------|--|-----------------------|
| A | EP,A,0 450 855 (ICI PLC) 9 October 1991 cited in the application see claims --- | 1,3 |
| A | WO,A,93 09272 (ALLIED SIGNAL INC) 13 May 1993 see claims --- | 1,3 |
| A | EP,A,0 454 109 (HOECHST AG) 30 October 1991 see claims; examples --- | 1,3 |
| A | US,A,5 023 010 (MERCHANT ABID N) 11 June 1991 see claims 1-10 --- | 1,3 |
| -/- | | |

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

Z document member of the same patent family

Date of the actual completion of the international search

24 May 1996

Date of mailing of the international search report

06-06-1996

Name and mailing address of the ISA

 European Patent Office, P.B. 3118 Patendlaan 2
 NL - 2220 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-3016

Authorized officer

Grittern, A

Form PCT ISA/210 (revised sheet) (July 1992)

page 1 of 2

INTERNATIONAL SEARCH REPORT

Date and Application No.

PCT/US 96/00336

| C(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT | | |
|---|---|-----------------------|
| Category * | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
| A | US,A,5 091 104 (VAN DER PUY MICHAEL) 25 February 1992 see claims 1-4,11-13 --- | 1,3 |
| A | US,A,3 278 615 (E.R. LARSEN ET AL.) 11 October 1966 see claim 1 --- | 1,10 |
| A | FR,A,2 287 432 (POUDRES & EXPLOSIFS STE NALE) 7 May 1976 cited in the application see claim 1 --- | 10 |
| A | DE,B,13 02 054 (FARBWERKE HOECHST AG) 5 February 1970 see claim 1 --- | 10 |
| A | DATABASE WPI Section Ch, Week 9117 Derwent Publications Ltd., London, GB; Class B03, AN 91-123600 XP002003769 & SU,A,1 427 780 (NOVOS ORG CHEM INST) . 15 September 1990 see abstract --- | 9 |
| A | US,A,3 882 182 (BENNINGER SIEGFRIED ET AL) 6 May 1975 see claims 5-8 ----- | 9 |

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/00336

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|---|---------------------|---|--|
| EP-A-0450855 | 09-10-91 | AU-B- 640760 AU-B- 7391391 CA-A- 2039828 JP-A- 5271692 NZ-A- 237628 | 02-09-93 10-10-91 05-10-91 19-10-93 26-07-94 |
| WO-A-9309272 | 13-05-93 | US-A- 5273592 AU-B- 2906892 | 28-12-93 07-06-93 |
| EP-A-0454109 | 30-10-91 | DE-A- 4013369 JP-A- 4227695 US-A- 5087383 | 31-10-91 17-08-92 11-02-92 |
| US-A-5023010 | 11-06-91 | NONE | |
| US-A-5091104 | 25-02-92 | NONE | |
| US-A-3278615 | 11-10-66 | BE-A- 683976 DE-A- 1568392 FR-A- 1493012 GB-A- 1121044 NL-A- 6609765 | 12-01-67 26-03-70 07-12-67 15-01-68 |
| FR-A-2287432 | 07-05-76 | NONE | |
| DE-B-1302054 | | BE-A- 690605 CH-A- 479514 DE-B- 1294949 DE-B- 1298514 DE-B- 1301807 FR-A- 1506638 NL-A- 6616938 | 02-06-67 15-10-69 28-02-68 05-06-67 |
| US-A-3882182 | 06-05-75 | DE-A- 2306438 BE-A- 810841 CA-A- 1006544 CH-A- 588442 FR-A,B 2217314 GB-A- 1438828 JP-A- 49102607 | 29-08-74 12-08-74 08-03-77 15-06-77 06-09-74 09-06-76 27-09-74 |

Form PCT/ISA/210 (patent family members) (July 1992)

15040 7.02/02

Inte. and Application No

Publication date

01-02-78
13-08-74

page 2 of 2